

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A63B 59/14, C08G 18/10, 18/32, 18/48, 18/76, 18/66	A1	(11) International Publication Number: WO 98/01189 (43) International Publication Date: 15 January 1998 (15.01.98)
(21) International Application Number: PCT/CA97/00419 (22) International Filing Date: 13 June 1997 (13.06.97) (30) Priority Data: 2,180,628 5 July 1996 (05.07.96) CA (71) Applicant (for all designated States except US): BAUER INC. [CA/CA]; Suite 600, 8000 boulevard Décarie, Montreal, Quebec H4P 2S4 (CA). (72) Inventor; and (75) Inventor/Applicant (for US only): BABICHUCK, Darrin [CA/CA]; 4978 Southview Avenue, Niagara Falls, Ontario L2H 2Z7 (CA). (74) Agents: GEORGIEV, Stephan, P. et al.; Smart & Biggar, Suite 3400, 1000 de la Gauchetière West, Montreal, Quebec H3B 4W5 (CA).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: HOCKEY STICK BLADE HAVING AN ABRASION RESISTANT COATING AND PROCESS FOR COATING SAID BLADE		
(57) Abstract <p>The invention relates to a hockey stick blade having an abrasion resistant coating, to a hockey stick comprising such a blade and to a process for coating a hockey stick blade. The coating is made from polyurethane or a mixture of polyurethane and polyurea and has a durometer hardness of at least about 70A. In a preferred embodiment, the coating may be made by mixing a urethane prepolymer having isocyanate terminal groups with an amine component. The coating of the present invention is particularly useful on harsh surfaces such as roller hockey surfaces and allows a player to use a stick that possesses better feel while reducing friction and abrasion.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LJ	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

**TITLE: HOCKEY STICK BLADE HAVING AN ABRASION RESISTANT
COATING AND PROCESS FOR COATING SAID BLADE**

FIELD OF THE INVENTION

5

The present invention relates to the field of hockey sticks and particularly to a hockey stick blade having improved wear properties. More particularly, the invention relates to a hockey stick blade comprising an abrasion resistant coating.

10

BACKGROUND TO THE INVENTION

15

The recent rise in popularity of in-line roller skates for use in leisure sport has also found it way into the field of hockey, the sport being commonly referred to as "in-line hockey" or "roller hockey". Traditionally, hockey has been practised on an ice rink whose surface is smooth and very slippery. Unlike ice hockey however, the surface on which roller hockey is played is somewhat harsh and as a result, increases the abrasion and the wear of the blade of a hockey stick. The harshness of the surface also means that the blade should exert as little friction as possible so as to be able to "glide" more easily on the surface of play.

20

25

In order to overcome the problems associated with abrasion, hockey stick manufacturers have suggested using stick blades made from various synthetic materials such as acrylonitrile-butadiene-styrene polymers (ABS) which are more resistant to wear. These hockey sticks have not however provided satisfactory results. Since traditional hockey sticks are constructed of wood, either alone or in combination with various composites such as fibreglass, carbon fibres or the like, they possess a certain feel to which hockey players have become accustomed. This "wood-like" feel is not present in the

30

conventional ABS roller hockey stick. Thus, the player is left with two unsatisfactory choices; either to play with a conventional hockey stick which provides the appropriate feel but that is subject to accelerated wear of the blade or to play with a synthetic stick that is more resistant to abrasion but that does not possess the appropriate feel.

In order to improve the wear properties of the blade, some manufacturers have also suggested using prepolymerized resins, such as phenoxy resins, dissolved in a volatile solvent such as a ketone. Other manufacturers have suggested using elastomeric coatings. These coatings have however been unsatisfactory for various reasons including, among others, their incapacity to resist wear over a relatively long period of time and their tendency to become brittle, i.e. their incapacity to deform before breaking when provided with a hardness that is high enough to adequately reduce friction. Yet another major disadvantage of using such coatings is the necessity to use organic solvents which are rather harmful to the environment and which have other associated disadvantages.

There is thus a need for a hockey stick blade comprising an abrasion resistant coating that will exhibit a level of hardness high enough to resist wear and adequately reduce friction without having a tendency to become brittle.

OBJECTS AND STATEMENT OF THE INVENTION

It is therefore an object of the present invention to provide a hockey stick blade which is more abrasion resistant than a conventional hockey stick blade.

A further object of the invention is to provide a hockey stick blade comprising an abrasion resistant coating having a hardness sufficient to prevent accelerated wear while adequately reducing friction.

5 As embodied and broadly described herein, the invention provides a hockey stick blade having a lower edge for contacting a surface of play, at least a portion of the lower edge bearing an abrasion resistant coating comprising polyurethane, the coating having a durometer hardness of at least about 70A.

10 In a preferred embodiment, the coating comprises polyurethane and polyurea, and most preferably, the coating is made by mixing a urethane prepolymer having isocyanate terminal groups with an amine component.

15 In one embodiment, the urethane prepolymer is made by reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an α,ω -glycol having between 2 and 6 carbon atoms, mixtures thereof or a low molecular weight polymer thereof and the amine component is a diamine which is mixed with an α,ω -glycol having between 2 and 6 carbon atoms or mixtures thereof.

20

 Most preferably, the urethane prepolymer is made by reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl) and the amine component is a mixture of 4,4'-methylene dianiline with an α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)].

25

 As embodied and broadly described herein, the invention also provides a hockey stick blade having a lower edge for contacting a surface of play, at least a portion of the lower edge bearing an abrasion resistant coating having a durometer hardness of at least about 70A, the coating being made by

30

5 mixing a urethane prepolymer with an amine component, the urethane prepolymer being made by reacting an approximately 80:20 mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an approximately 90:10 mixture of two α -hydro- ω -hydroxypoly (oxy-1,4-butanediyls) having molecular weights of about 1000 and about 2000, respectively, the amine component being a mixture of 4,4'-methylene dianiline with an approximately 75:25 mixture of two α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyls)] having molecular weights of about 1000 and about 500, respectively.

10 In another embodiment, the coating is made by mixing a diisocyanate with an amine mixture comprising an amine component, an α,ω -glycol having between 2 and 6 carbon atoms, mixtures thereof or a low molecular weight polymer thereof. Preferably, the diisocyanate is diphenylmethane diisocyanate and the amine mixture comprises an α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl), 4,4'-methylene dianiline and an α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)].

In a preferred embodiment, the coating has a durometer hardness between about 70A and 75D.

20

Preferably, the coating is between 20 to 30 mils thick and may comprise a pigment.

25

In another aspect, the invention also provides a hockey stick comprising a blade coated in accordance with the teachings of the present invention.

30

As embodied and broadly described herein, the invention also provides a process for coating a hockey stick blade, the process comprising the step of applying to a blade a coating comprising polyurethane and having a

durometer hardness of at least 70A, the process being carried out in the absence of or substantially in the absence of solvent.

In a preferred embodiment, the process comprises the steps of:

- 5 a) reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an α,ω -glycol having between 2 and 6 carbon atoms, mixtures thereof or a low molecular weight polymer thereof to form a urethane prepolymer;
- 10 b) mixing a diamine with an α,ω -glycol having between 2 and 6 carbon atoms or mixtures thereof to provide an amine component;
- c) mixing the urethane prepolymer and the amine component to form a coating composition; and
- d) applying the composition to the blade.

15 In a preferred embodiment, the urethane prepolymer and the amine component are heated to a temperature of about $70^{\circ}\text{C} \pm 10^{\circ}\text{C}$ before being admixed and applied to the blade.

 Most preferably, the urethane prepolymer of step a) is made by
20 reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl) and the amine component of step b) is a mixture of 4,4'-methylene dianiline with an α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)]. Preferably, the process is carried out in the absence of or substantially in the absence of solvent.

25 The blade coated in accordance with the invention has the advantage of preventing accelerated wear due to harsher playing surfaces while reducing friction. The inventor has also discovered that the coating of the present invention is advantageous when used on traditional ice hockey rinks.

30 Indeed, although ice surfaces are not as harsh as roller hockey surfaces, ice hockey stick blades are nonetheless subjected to abrasion. This condition

should be avoided since as a result of the abrasion, water tends to penetrate inside the blade and reach the fibreglass, if any, thereby contributing to the delamination of the components of the stick which, over time, induces structural failure to the stick. This problem may be avoided by providing an ice hockey stick blade with the coating of the present invention.

Other objects and features of the invention will become apparent by reference to the following description of a preferred embodiment.

DESCRIPTION OF A PREFERRED EMBODIMENT

The inventors have discovered that the objects of the present invention could be achieved by providing a coating having a durometer hardness of at least about 70A when measured in accordance with the ASTM D-2240 test. More precisely, the inventors have realized that a suitable coating having such properties may be obtained by using a composition comprising polyurethane or a mixture of polyurethane and polyurea.

In accordance with a preferred embodiment of the invention, a coating is provided on the lower edge of the blade of a hockey stick. For the purpose of this specification, the expression "lower edge" is intended to cover the portion of the blade that is in contact with a surface of play. The coating can be applied on the entire edge or simply on the area that contacts the surface of play such as, for example, the heel portion. Similarly, the blade could be provided with a coating that is thicker at the heel portion and thinner at the front portion. In yet another embodiment, the coating could be applied on the entire blade.

A coating according to a first embodiment of the invention may consist of a polyurethane made by reacting an isocyanate and a polyol.

5

15

25

photochemical degradation and accelerated oxidation of the coating as a result of exposure to UV radiation, there may also be provided a UV stabilizer. Both the choice and the type of UV stabilizer may be determined by the person skilled in the art. Other additives such as fillers, antioxidants, thickeners or emulsifiers may also be included in the composition.

The coating should be within the specified range since a coating having a durometer hardness below about 70A may be too soft and may not allow the player to benefit from the reduced friction. On the other hand, the inventor has realized that a coating having a durometer hardness above about 75D may have a tendency to become brittle and as a result, the durometer hardness of the coating should not exceed 75D. However, the person skilled in the art will realize that the maximum value for the hardness may only depend on the desired applications and this limitation should not be interpreted in a limiting manner.

The person skilled in the art will realize that it is possible to adjust the hardness of the coating by using various additives or by modifying the type of isocyanate or polyol so that the durometer hardness will fall within the scope of the present invention. Such modifications may be determined by routine testing.

A coating according to a second embodiment of the present invention comprises a mixture of polyurethane and polyurea and is made from mixing a urethane prepolymer with an amine component. It may also comprise further additives such as the ones previously mentioned.

The urethane prepolymer is prepared by reacting an isocyanate with a polyol as described in relation with the first embodiment. The hydroxy groups of the polyol will thus react with the isocyanate groups of the diisocyanate to form a urethane prepolymer. However, unlike the first

embodiment in which the coating comprises only polyurethane and additives, if any, the molar ratio of the polyol to the isocyanate is determined so that the urethane prepolymer will have isocyanate terminal groups, hence the use of the expression "prepolymer". Preferably, the ratio of polyol to isocyanate is chosen so that there will be between 6% to 10% excess diisocyanate in the urethane prepolymer.

The isocyanate terminal groups of the urethane prepolymer are then mixed with an amine component to form a coating composition comprising a mixture of polyurethane and polyurea.

The amine component is preferably a diamine. Suitable diamines include α,ω -alkylenediamine having preferably between 2 to 6 carbon atoms and aromatic diamines such as 4,4'-methylene bis(2-chloroaniline), 2,4-toluene diamine, diethyl or 4,4'-methylene dianiline.

While it is possible to mix the urethane prepolymer directly with the amine component, it is however preferable, for handling purposes, if the amine component is mixed with a suitable glycol that acts as a chain extender. Thus, the amine component may be a diamine mixed with an α,ω -glycol having between 2 and 6 carbon atoms or mixtures thereof. Most preferably, the mixture is obtained by mixing equal amounts of 4,4'-methylene dianiline with an approximately 75:25 mixture of two α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyls)] having a molecular weight of about 1000 and about 500, respectively.

The person skilled in the art will realize that it may be possible to use other amine components or mixtures provided that the stoichiometric ratio is adjusted to take into consideration the variations in molecular weight. Examples of other suitable amine components include 4,4'-methylene bis(2-

chloroaniline) or 2,4-toluene diamine, diethyl. Similarly, other glycols, such as α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl) could be used.

5 Additives, such as the ones described in relation with the first embodiment may also be used.

The invention will be further understood by the description of the following example that constitutes a preferred embodiment of the invention and that should not be construed in a limiting manner:

10

Example 1

COMPOSITION

15

Ingredient

% by weight

Mixture A (urethane prepolymer)

MONDUR TD-80 ¹

~30

TERATHANE 1000 and 2000 ²

~60

20

mixture B (amine component and additives)

4,4'-methylene dianiline

~5

α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)] ³

~5

carbon black

~0.25

25

¹ approximately 80:20 mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate.

² approximately 90:10 mixture of two α -hydro- ω -hydroxypoly (oxy-1,4-butanediyls) having molecular weights of about 1000 and about 2000, respectively.

30

³ approximately 75:25 mixture of two α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyls)] having molecular weights of about 1000 and about 500, respectively.

The ingredients of mixture A were mixed together in a first chamber and were heated to a temperature of about $70^{\circ}\text{C} \pm 10^{\circ}\text{C}$. Similarly, the ingredients of mixture B, including any other additives, were mixed together in a second chamber and were also heated to a temperature of about $70^{\circ}\text{C} \pm 10^{\circ}\text{C}$.

35

Mixtures A and B were then mixed together in a 2:1 ratio (two part mixture A and one part mixture B) and the resulting composition was applied to a wood hockey stick blade by using a spray gun. A PROBLER gun (Product of Glas-Craft) with a 17:1 fluid to air ratio was found to be suitable for this. The use of such a spray gun facilitates the coating operation since the two mixtures A and B are only mixed at the tip of the gun thereby preventing premature solidification of the composition. In a variant, the tip of the spray gun may be removed and the composition may be applied as a bead. The person skilled in the art will however realize that the composition may be applied to the blade using other similar equipment or other coating techniques known in the art. A preferred thickness for roller hockey is approximately from 10 to 50 mils and preferably from 20 to 30 mils but the thickness may vary according to the intended use. Also, the coating may be applied in a single application or in a series of applications. In the latter case however, each coating is not left to dry before the other coating is applied.

The composition was then left to dry under normal conditions and solidified thereby providing an abrasion resistant coating. A period of between 40 to 60 seconds was found to be sufficient to complete the drying.

PHYSICAL PROPERTIES

The coating of example 1 exhibited the following properties:

	Property	Result	Test
5	Hardness (durometer Shore D)	50D±5D ¹	ASTM D-2240
	Tensile strength (psi)	3200	ASTM D-412
	Elongation (%)	300	ASTM D-412
	Resiliency (%)	45	ASTM D-2632

10 ¹ This value is equivalent to a durometer hardness of at least 90A.

The coating of example 1 was tested on pavement and on an ice rink and provided satisfactory results.

15 While the coating of the second embodiment was prepared by a urethane prepolymer with an amine component, in yet a third embodiment, the coating could be prepared by mixing a diisocyanate with a mixture comprising a polyol, an amine component and additives, if any. For apparent reasons, a less dangerous diisocyanate such as diphenylmethane diisocyanate should preferably be used in such an embodiment instead toluene-2,4-diisocyanate and toluene-2,6-diisocyanate.

20

Because of the relatively fast solidification time of the composition, the use of the coating of the present invention may improve the efficiency of the manufacturing process of hockey stick blade thereby lowering costs.

25 Furthermore, the use of the coating according to the invention avoid the use of volatile organic compounds which might be released into the atmosphere and is thus safer for the environment.

The above description of a preferred embodiment should not be interpreted in any limiting manner since variations and refinements are possible which are within the spirit and scope of the present invention. The scope of the invention is defined in the appended claims and their equivalents.

THE EMBODIMENTS OF THE INVENTION FOR WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

5 1. A hockey stick blade having a lower edge for contacting a surface
of play, at least a portion of said lower edge bearing an abrasion resistant
coating comprising polyurethane, said coating having a durometer hardness of
at least about 70A.

10 2. A blade as defined in claim 1 wherein said coating comprises
polyurethane and polyurea.

15 3. A blade as defined in claim 2 wherein said coating is made by
mixing a urethane prepolymer having isocyanate terminal groups with an amine
component.

20 4. A blade as defined in claim 3 wherein said urethane prepolymer
is made by reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-
diisocyanate with an α,ω -glycol having between 2 and 6 carbon atoms,
mixtures thereof or a low molecular weight polymer thereof and wherein said
amine component is a diamine which is mixed with an α,ω -glycol having
between 2 and 6 carbon atoms or mixtures thereof.

25 5. A blade as defined in claim 4 wherein said urethane prepolymer
is made by reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-
diisocyanate with an α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl) and wherein
said amine component is a mixture of 4,4'-methylene dianiline with an α -hydro-
 ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)].

30 6. A hockey stick blade having a lower edge for contacting a surface
of play, at least a portion of said lower edge bearing an abrasion resistant
coating having a durometer hardness of at least about 70A, said coating being

made by mixing a urethane prepolymer with an amine component, said urethane prepolymer being made by reacting an approximately 80:20 mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an approximately 90:10 mixture of two α -hydro- ω -hydroxypoly (oxy-1,4-butanediyls) having molecular weights of about 1000 and about 2000, respectively, said amine component being a mixture of 4,4'-methylene dianiline with an approximately 75:25 mixture of two α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyls)] having molecular weights of about 1000 and about 500, respectively.

7. A blade as defined in claim 1 wherein said coating is made by mixing a diisocyanate with an amine mixture comprising an amine component, an α , ω -glycol having between 2 and 6 carbon atoms, mixtures thereof or a low molecular weight polymer thereof.

8. A blade as defined in claim 7 wherein said diisocyanate is diphenylmethane diisocyanate and wherein said amine mixture comprises an α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl), 4,4'-methylene dianiline and an α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)].

9. A blade as defined in claim 1 wherein said coating is between 20 to 30 mils thick.

10. A blade as defined in claims 1, 2, 3, 4, 5, 6, and 7, wherein said coating has a durometer hardness between about 70A and about 75D.

11. A hockey stick comprising a blade coated in accordance with any claim 1.

12. A process for coating a hockey stick blade, said process comprising the step of applying to a blade a coating comprising polyurethane

and having a durometer hardness of at least 70A, said process being carried out in the absence of or substantially in the absence of solvent.

13. A process for coating a hockey stick blade, said process comprising the steps of:

- a) reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an α,ω -glycol having between 2 and 6 carbon atoms, mixtures thereof or a low molecular weight polymer thereof to form a urethane prepolymer;
- b) mixing a diamine with an α,ω -glycol having between 2 and 6 carbon atoms or mixtures thereof to provide an amine component;
- c) mixing said urethane prepolymer and said amine component to form a coating composition; and
- d) applying said composition to said blade.

14. A process as defined in claim 13 wherein said urethane prepolymer and said amine component are heated to a temperature of about $70^{\circ}\text{C} \pm 10^{\circ}\text{C}$ before being admixed and applied to said blade.

15. A process as defined in claim 14 wherein the urethane prepolymer of step a) is made by reacting a mixture of toluene-2,4-diisocyanate and toluene-2,6-diisocyanate with an α -hydro- ω -hydroxypoly (oxy-1,4-butanediyl) and wherein the amine component of step b) is a mixture of 4,4'-methylenedianiline with an α -hydro- ω -hydroxypoly [oxy(methyl-1,2-ethanediyl)].

16. A process as defined in claims 13 or 14, said process being carried out in the absence of or substantially in the absence of solvent.

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A63B59/14 C08G18/10 C08G18/32 C08G18/48 C08G18/76
C08G18/66

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A63B C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 332 212 A (SUSI MICHAEL F ET AL) 26 July 1994 see claims 1,2,7 see column 2, line 25 - column 3, line 16 ---	1
X	FR 2 487 208 A (BONIFACE JACQUES) 29 January 1982 see claims 1,3 see page 2, line 9 - line 22 ---	1
X	WO 96 02385 A (FULLER H B LICENSING FINANC) 1 February 1996 see claims 1-5 see page 1, line 26 - page 2, line 31 --- -/--	1,2



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

10 October 1997

Date of mailing of the international search report

24.10.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Puymbroeck, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 97/00419

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 288 823 A (AIR PROD & CHEM) 2 November 1988 see claims 1,2,5,6 see example 1	1
A	--- EP 0 164 523 A (AMERICAN CYANAMID CO) 18 December 1985 see claims 1-6	1
A	--- EP 0 073 034 A (DATAPRODUCTS CORP) 2 March 1983 see claims 1-9 -----	1

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5332212 A	26-07-94	NONE	
FR 2487208 A	29-01-82	NONE	
WO 9602385 A	01-02-96	NONE	
EP 0288823 A	02-11-88	US 4786703 A	22-11-88
		JP 2517744 B	24-07-96
		JP 63278923 A	16-11-88
EP 0164523 A	18-12-85	US 4556703 A	03-12-85
		CA 1253286 A	25-04-89
		DE 3583967 A	10-10-91
		JP 1877367 C	07-10-94
		JP 6002794 B	12-01-94
		JP 60245624 A	05-12-85
EP 0073034 A	02-03-83	US 4404353 A	13-09-83
		AU 8725982 A	03-03-83
		CA 1208232 A	22-07-86
		JP 1029491 B	12-06-89
		JP 1543446 C	15-02-90
		JP 61281117 A	11-12-86
		JP 1432733 C	24-03-88
		JP 58052318 A	28-03-83
		JP 62033244 B	20-07-87

THIS PAGE BLANK (USPTO)